



FIRE RETARDANT PAINT

LATEX INTUMESCENT COATING

FLAT FINISH FR-110

Features

- Intumescent product
- Flame Spread Rating: Class "A" when tested in accordance with ASTM E-84 (NFPA 255) and S-102.
- Applies like a regular paint
- Soap and water cleanup
- Low VOC

General Description

Insl-x® Fire Retardant Paint is a high-quality latex decorative, intumescent, fire retardant coating for interior ceilings, walls and trim. This product provides a high-hiding flat finish that retards flame spread by reacting to heat and forming a thick cellular char blanket (intumescence). By reducing excessive heat penetration, this product retards flame spread and minimizes smoke generation. It is suitable for primed or previously painted wood, drywall, cellulose tile, cured plaster, masonry and metal. It applies like a conventional latex paint, low in VOCs, and washes without spotting.

Recommended For

For interior use on primed or previously painted wood, drywall, cellulose tile, cured plaster, masonry and metal. NOTE: Top coating this product will reduce its intumescent properties.

Limitations

- Use product when surface temperature is between 50 °F (10 °C) and 95 °F (35 °C).

Product Information

Colors — Standard:

White FR-110
Can be tinted with up to 2 oz. of Universal Colorants.

— Tint Bases:

NA

— Special Colors:

Contact your dealer.

Certifications & Qualifications:

VOC compliant in all regulated areas

The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (0.42 lbs./gal.) excluding water & exempt solvents.

This product meets qualifications for LEED (Leadership in Energy and Environmental Design) projects as a Flat Coating.

Master Painters Institute MPI # 64



UL Flame Spread Rating: Class "A"; tested in accordance with ASTM E-84-10/30 (NFPA 255) and S-102; tested over Douglas fir.

Standard 10 Minute Test Results

Flame Spread Index	0
Smoke Developed Index	35

30 Minute Extended Test Results:

Flame Spread Index	Pass
Smoke Developed Index	Pass

Technical Assistance:

Available through your local authorized independent Insl-x dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit www.insl-x.com

Technical Data

White

Vehicle Type	Vinyl Acrylic	
Pigment Type	Titanium Dioxide	
Volume Solids	46.0 ± 1.0%	
Coverage per Gallon and per coat at Recommended Film Thickness	<p>Note: 10 minute burn class A rating. ASTM-E-84 with spread rate: 2 coats at 300-330 square feet/gallon (4.7-5.2 mils WFT and 2.2-2.4 mils DFT each)</p> <p>Note: 30 minute burn class A rating. ASTM E-84 with spread rate: 2 coats at 150-165 square feet/gallon (9.5-10.4 mils WFT and 4.4-4.8 mils DFT each).</p>	
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		
Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	30 Minutes
	– To Recoat	4 Hours
High humidity and cool temperatures will result in longer dry, recoat and service times.		
Dries By	Coalescence	
Viscosity	70 – 80 KU	
Flash Point	N/A	
Gloss / Sheen	Flat (<10 @ 85°)	
Surface Temperature at Application	– Min.	50 °F
	– Max.	95 °F
Thin With	Not Necessary	
Clean Up Thinner	Warm, Soapy Water	
Weight Per Gallon	10.8 lbs.	
Storage Temperature	– Min.	50 °F
	– Max.	90 °F
Volatile Organic Compounds (VOC)		
	45 Grams/Liter	0.37 Lbs./Gallon

◇ Reported values are for White, Contact dealer for values of other bases or colors.

Fire Retardant Paint Latex Flat Finish FR-110

Surface Preparation

Surfaces to be painted must be clean, dry and free of oil, grease, dust, rust, mill scale, loose paint, chalk and other contaminants that could interfere with adhesion. Glossy surfaces should be dulled by abrading the surface.

Previously Painted Surfaces: No primer is needed if surface is in good condition. Clean and sand as needed.

Ferrous Metal: Remove loose rust and mill scale with a grinder, scraper, wire brush or sandpaper. Remove oil and grease as necessary using an oil and grease emulsifying cleaner. Prime bare spots with metal primer.

Wood/Drywall: Spot prime patched and spackled areas with the recommended primer before top-coating.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir this product thoroughly before use. Once stirred, Insl-x Fire Retardant Paint is ready to use. Do not incorporate any additives into this product and thin with water only as needed. Do not apply if surface or air temperatures are below 50 °F or above 95 °F.

Brush: Synthetic Bristle only.

Roller: 3/8" to 1/2" Nap Synthetic Roller

Airless Spray: Fluid Pressure – 1500 to 2500 psi.
Tip Size - .013 to .017

Clean Up

Clean all equipment immediately after use with soap and water. Spray equipment should be given a final rinse with mineral spirits to prevent corrosion.

Environmental Health & Safety Information

Not a hazardous substance or mixture according to the Globally Harmonized System (GHS)

Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling. Refer to Safety Data Sheet for additional health and safety information.



WARNING Cancer and Reproductive Harm–
www.P65warnings.ca.gov

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP OUT OF REACH OF CHILDREN
KEEP FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**